



# WORLD CLASS™ 2.1 VOC EURO CLEAR

## TECHNICAL DATA SHEET



Check local VOC regulations to ensure compliance of all products in your area.

### DESCRIPTION

World Class 2.1 VOC Euro Clear is a higher solids, 2.1 VOC compliant, two-component clearcoat for collision shops in regulated areas.

### FEATURES

- 24 month warranty
- Great product at mid-grade price
- Exceptional appearance
- Chemical resistant
- Easy to buff
- Excellent UV protection

### SUITABLE SUBSTRATES

- All automotive basecoat paint systems
- Fully cured refinish materials
- Properly prepped OEM finishes

### TYPICAL PROPERTIES

Part:	Product Name:	Color:	Container:
50709	World Class 2.1 VOC Euro Clear	Clear	5 Liter
RTS weight solids:		41.2%	
RTS volume solids:		38.8%	
RTS VOC:		Max 2.1 #/gal (252 g/L)	
Pot life:		30 min (50752) 1 hour (50762, 50772) @ 70°F (21°C) and 50% RH	
Fluid tip size:		1.3 – 1.4	
Inlet air pressure:		25 – 35 psi	
Coverage:		311 sq.ft./gal @ 2 mils DFT	
Dust time:		10-30 minutes	
Air dry time to buff:		4-8 hours	

### HANDLING AND APPLICATION

#### PREPARATION:

After sanding primer, scuff any blend areas with **Scuff & Clean** according to directions. Clean surface with **SEM**



Check local VOC regulations to ensure compliance of all products in your area.

**Solve** or **XXX Universal Surface Cleaner**. Apply basecoat per instructions and allow to fully flash dry.

### MIXING:

Shake or stir thoroughly. Mix by volume:

2 Parts	1 Part
2.1 VOC Euro Clear	2.1 VOC Euro Activator

### ACTIVATORS:

Part:	Product Name:	For:
50752	2.1 VOC Euro Fast Activator	Small parts, 1-2 panels. Larger jobs from 55°F (13°C)
50762	2.1 VOC Euro Medium Activator	2-3 panels. Larger jobs from 65°F (18°C)
50772	2.1 VOC Euro Slow Activator	3-5 panels. Larger jobs from 75°F (23°C)

### ADDITIVES:

Part:	Product Name:	For:
50918	Accelerator	Reducing cure to handle times by up to 25%
50928	Extender	Extending pot life in hot and/or humid conditions

### Note:

The use of **Accelerator** may reduce time to buff by up to 30 minutes. For best performance when using **Accelerator**, complete buffing operation within 16-24 hours.

Thinning with reducer is not recommended. If used, amount should not exceed 5% by volume.

### APPLICATION:

1. Set air pressure to 8-10 psi at the cap for HVLP equipment.
2. Use a spray gun equipped with a 1.3–1.4 fluid nozzle.
3. Spray two full coats, allowing 5-15 minutes between coats.

Allow 10 minute flash after last coat prior to force drying.

### DRY TIMES:

#### Note:

Dry and cure times are dependent on several factors including temperature, air-flow, film build, activator selection and humidity.

	Air Dry	Force Dry 20 min @140°F (60°C)
To handle:	3-8 hours	After cool down
To buff:	4-8 hours	After cool down



Check local VOC regulations to ensure compliance of all products in your area.

---

**To deliver:** 8-24 hours After cool down

---

**Note:**

If recoating with clear only, sand with 1000 grit. If re-applying basecoat and clearcoat, sand with 600 grit.

**CLEANUP:**

Use **XXX Gun Cleaner** or appropriate cleaning materials compliant with VOC regulations in your area.

**STORAGE:**

**World Class 2.1 VOC Euro Clear** should be stored in a cool dry place with adequate ventilation away from heat, sparks and flames. The shelf life for **World Class 2.1 VOC Euro Clear** is 5 years when stored under normal conditions. The shelf life for **World Class 2.1 VOC Euro Activators** is 3 years.

**RELATED PRODUCTS:**

<b>Part:</b>	<b>Product Name:</b>	<b>Size:</b>
38371	SEM Solve	Gallon
38373	SEM Solve	20 oz. Aerosol
38374	SEM Solve	Quart
38375	SEM Solve	5 Gallon
38391	Scuff & Clean	Gallon
38398	Scuff & Clean	16 oz. Tube
50752	2.1 VOC Euro Fast Activator	2.5 Liter
50762	2.1 VOC Euro Medium Activator	2.5 Liter
50772	2.1 VOC Euro Slow Activator	2.5 Liter
50918	Accelerator	Pint
50928	Extender	Pint
77743	XXX Gun Cleaner	20 oz. Aerosol
77763	XXX Universal Gun Cleaner	20 oz. Aerosol
77771	XXX Universal Surface Cleaner	Gallon
77774	XXX Universal Surface Cleaner	Quart