



MINI-MAX BUMPER REPAIR

TECHNICAL DATA SHEET



Check local VOC regulations to ensure compliance of all products in your area.

DESCRIPTION

Mini-Max Bumper Repair is a two component epoxy based filler for repairing small damage to bumpers and rigid or semi-rigid plastics.

FEATURES

- No adhesion promoter necessary
- Superior adhesion
- Excellent sanding and feather edge
- Does not shrink or pinhole
- Zero VOC

SUITABLE SUBSTRATES

- Olefin-based plastics
- Rigid and semi-rigid plastics

TYPICAL PROPERTIES

Part:	Product Name:	Color:	Container:
68422	Bumper Repair	Gray	1 oz. Mini-Max Cartridge

Working time:	5 minutes @70°F (21°C)
Sand time:	15 minutes @70°F (21°C)
Top coat time:	20 minutes @70°F (21°C)
Cure time:	1 hour @70°F (21°C)

HANDLING AND APPLICATION

PREPARATION:

1. Clean with Scuff & Clean and a gray scuff pad. Rinse with water and dry.
2. Clean with Plastic & Leather Prep.
3. Sand with 80 grit paper 2-3 inches around damaged area.
4. "V" groove damaged area with a 24 or 36 grit disc. Grind slowly. Excess heat may seal the pores of the plastic making adhesion difficult.

MIXING:

Remove cap between pistons. Cut off cartridge tips at perforation. Dispense material and mix until uniform.



Check local VOC regulations to ensure compliance of all products in your area.

APPLICATION:

1. Reinforce large holes and damaged areas from the back side with **Plastic Repair Reinforcing Tape** or **Plastic Repair Contouring Tape**. In such cases, clean the back side of the area with **Scuff & Clean** and **Plastic & Leather Prep**. Grind with a 24 or 36 grit disc at low RPM. Place **Plastic Repair Reinforcing Tape** or **Plastic Repair Contouring Tape** over the repair. Apply **Mini-Max Bumper Repair** and spread firmly.
2. Next, after the backside repair has set, apply **Mini-Max Bumper Repair** to the front repair area. Press firmly to eliminate air pockets. Apply higher than surrounding area to allow for sanding.
3. After **Mini-Max Bumper Repair** has cured for 15 minutes, sand first with 80 grit, then finish with 180 grit paper.
4. For slight imperfections, reapply a skim coat of **Mini-Max Bumper Repair** or use **Bumper Bite Flexible Glaze**.
5. To fill sand scratches and prepare surface for painting, apply **Flexible Primer Surfacer**, **High Build Primer Surfacer** or **World Class™ Waterborne Flexible Primer**.

Note:

For larger repairs, **Problem Plastic Repair Material** in the 7 oz. **Dual-Mix** cartridge is also available.

STORAGE:

Mini-Max Bumper Repair should be stored in a cool dry place with adequate ventilation away from heat, sparks and flames. The shelf life for **Mini-Max Bumper Repair** is 1 year when stored under normal conditions.

RELATED PRODUCTS:

Part:	Product Name:	Size:
38331	Scuff & Clean	Gallon
38338	Scuff & Clean	Pint
38351	Plastic & Leather Prep	Gallon
38353	Plastic & Leather Prep	Aerosol
38354	Plastic & Leather Prep	Quart
70006	Plastic Repair Reinforcing Tape	36" Roll
70007	Plastic Repair Contouring Tape	15" Roll
40482	Bumper Bite Flexible Glaze	Tube
39131	Flexible Primer Surfacer	Gallon
39133	Flexible Primer Surfacer	Aerosol
39134	Flexible Primer Surfacer	Quart
42003	High Build Primer Surfacer	Aerosol
42013	High Build Primer Surfacer	Aerosol
42023	High Build Primer Surfacer	Aerosol
42033	High Build Primer Surfacer	Aerosol
42043	High Build Primer Surfacer	Aerosol



Check local VOC regulations to ensure compliance of all products in your area.

50184	Waterborne Flexible Primer	Quart
39767	Problem Plastic Repair Material	7 oz. Cartridge
