
PRODUCT INFORMATION

4361, 4364

Quick Dry Rubberized Undercoat

DESCRIPTION:

Quick Dry Rubberized Undercoat is a rapid-drying highly protective automotive coating for autobody interiors and underhood applications. Resists rust and abrasion as it seals out dust and moisture. Deadens sound. Excellent adhesion to painted and unpainted surfaces.

APPLICATION:

Stir thoroughly before use. Wash and solvent clean surface to remove all rust, dirt and grease. Apply with a gun, using air pressure of 40 PSI at the gun. Allow to dry at least 4 hours before painting. Thoroughly clean gun with Acry Solvent #9783/9784 immediately after use. May be topcoated after an hour.

NOTE: This product contains asphalt which may stain light colored topcoats.

SALES POINTS:

- Fast drying, easy to apply.
- Excellent abrasion resistance.
- Retains black color.
- Won't sag or run.
- Dries completely, yet remains flexible.
- Seals out dust, fumes, heat and cold.
- Aerosol package requires no clean-up.

COMPETITION:

3M Body Schutz
FE Rubberized Undercoating
Rusfree Rubberized Undercoating

(Refer to Material Safety Data Sheet for proper handling of products listed in this bulletin).

PACKAGE SIZE:

#4361 Quick Dry Rubberized Undercoat, Gallon (3.78 L), 2/case
#4364 Quick Dry Rubberized Undercoat, Quart (0.946 L), 6/case

DISCLAIMER: The technical information and suggestions for use have been compiled for your guidance and usage. Such information is based on Transtar Autobody Technologies experience and research and is believed to be reliable. As Transtar has no control over conditions in which the product is used, stored, or otherwise handled, the above information does not constitute a warranty. Buyers must assume responsibility for the suitability of the product for their purposes.



Quick Dry Rubberized Undercoat is a rapid-drying highly protective automotive coating for autobody interiors, underhood and underbody applications. Resists abrasion and inhibits rust as it seals out dust and moisture. Deadens sound. Excellent adhesion to painted and unpainted surfaces.

SUITABLE SUBSTRATES

Substrate		Substrate		Substrate	
Painted or Primed Steel	✓	Galvanized Steel	✓	Painted or Primed Aluminum	✓
Bare Steel	✓	Bare Aluminum	✓		

MIXING



Mix Ratio: Ready to Spray

Pot Life: N/A

SURFACE PREPARATION



Clean with SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394.

APPLICATION



AEROSOL:

Shake well. Wash and solvent clean surface to remove all rust, dirt and grease using SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394. Hold can in an upright position and spray 8-10 inches from surface, using steady light strokes. Several light coats will produce a better finish than one heavy coat. Remove overspray with Acry Solvent 9783/9784. May be topcoated after one hour.



QUART/GALLON:

Stir thoroughly before use. Wash and solvent clean surface to remove all rust, dirt and grease. Apply with a shutz gun, using the gun manufacturer's recommended air pressure. Allow to dry at least 4 hours before painting. Thoroughly clean gun with Acry Solvent 9783/9784 immediately after use. May be topcoated after an hour.

NOTE: This product contains asphalt which may stain light colored topcoats.

PRODUCT SPECIFICATIONS

Color: Black	Shelf Life: 1 year
Size: Gallon (4361-F), Quart (4364-F), 24 oz Aero (4363-F)	

REGULATORY:

Category: Underbody Coating	4361-F/4364-F	Category: Undercoating	4363-F
VOC Actual	2.74#/gal (328 g/l)	VOC Content	<40% by weight
VOC Regulatory	3.58#/gal (429 g/l)		
Weight % of Volatiles	55.78		
Weight % of Water	0.1		
Weight % of Exempt Compounds	20.08		
Volume % of Exempt Compounds	23.35		
Density of Material #/gal	7.69		