



DRIVING SURFACE PERFECTION™

TRIM#11



TECHNICAL DATA SHEET

HIGH BUILD TOP COAT AEROSOL

Version: 2.2

TECHNICAL DATA SHEET & PROCESS GUIDE

Restores original appearance to body panels, under hood, chassis and wheels.

- Suitable for use over existing paint surfaces
- Replicates factory look on aluminum and plastic trim panels
- High gloss, satin, matte or metallic finish
- Excellent pigment density, essentially single coat coverage
- Apply direct to TPO, EDPM, and polypropylene without adhesion promotor

TECHNICAL DATA AND APPLICATION GUIDE



Substrates

- Prepared OEM painted surfaces
- TPO, EDPM, polypropylene
- Lightly abraded E coat



Tools Required

- U-POL System 20 Degreaser (UP2002, UP2012, UP2022)
- 400-600 Grit Sandpaper



Substrate Preparation

For best results, ensure the surface is thoroughly cleaned, degreased, dried and dust free. Sand primed surfaces wet or dry with 400-600 grit sandpaper, degrease and dry.



Mixing

Shake the aerosol can for at least 2 minutes before use.



Coats

1 - 2 coats at a distance of approx. 6 - 10 inches from the surface.

Build 15µ / 0.6 MIL

*Theoretical Coverage approx. ft²/CAN 48.4

**Theoretical Coverage per unit assuming 100% transfer efficiency and giving the dry film thickness between indicated values.*



Flash-off / min @ 68°F

between coats 3 -5 mins



Drying Times

Dust free @ 68°F / min 20 - 30 minutes



DRIVING SURFACE PERFECTION™

TRIM#11



TECHNICAL DATA SHEET

HIGH BUILD TOP COAT AEROSOL

Version: 2.2

TECHNICAL DATA SHEET & PROCESS GUIDE

STORAGE & VOC INFORMATION



Shelf Life

2 years subject to proper storage conditions.

Aerosol cans should be stored for two hours at room temperature before use. For long term storage, keep in a dry well ventilated area and away from direct sunlight and frost. To maximize the lifespan of your aerosol, always invert the can and spray upside down for a few seconds after each use to clear the nozzle. If the nozzle becomes blocked, remove it from the can and soak it in gentle thinners.

Recommended Storage Temperature 41°F - 77°F

Recommended Application Temperature 68°F



VOC Information

Order Code	Format	Color	MIR
UP0876	450ml Aerosol	Gloss Black	CARB ABT 1.7
UP0877	450ml Aerosol	Matte Black	CARB ABT 1.7
UP0878	450ml Aerosol	Satin Black	CARB ABT 1.7
UP0879	450ml Aerosol	Gloss White	CARB ABT 1.7
UP0880	450ml Aerosol	Steel Wheels	CARB ABT 1.7
UP0881	450ml Aerosol	Silver Wheels	CARB ABT 1.7

IMPORTANT: FOR PROFESSIONAL USE ONLY. Read full instructions before use.

This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the safety data sheet for full handling instructions and personal protection information. U-POL disclaims any liability where the user does not wear the recommended personal protective equipment. The above data is for information only and may change without prior notice. It is the Buyers responsibility to ensure the suitability of the products for their own use and check the information is up to date. The recommendation of use of our products and application in our technical data sheets are based on our knowledge and experience. These data sheets are available via your local distributor or via the U-POL website. U-POL is not responsible for the results obtained by others over whose methods we have no control and thereof U-POL is not liable for consequential or incidental damages including loss of profits.